

CRYOGELS BASED ON POLYELECTROLYTE COMPLEX BETWEEN CHITOSAN AND GELATIN FORMED UNDER CRYOCONDITIONS FOR TISSUE ENGINEERING

Dmitriy Berillo^{1, 2}, Yishan Zheng² and Irina N. Savina²

¹ Nazarbaev University, Laboratory of Biosensors and Bioinstruments, PI "National Laboratory Astana", Kazakhstan

² University of Brighton, Biomaterials and Medical Devices Research, School of Pharmacy and Biomolecular Sciences, United Kingdom

Cryogelation technique is a versatile technique for design of various biocompatible scaffolds based on natural polymers as gelatin(Gel), chitosan and casein using cryogelation technique. [1-4] Cryogelation is the process of the formation of macroporous polymer systems, so called cryogels, with well-developed 3D structure of interconnected pores. Cryogels have porosity of 90-95% and macro-channels of 20-150 μm in size. Interconnected pores provide unrestricted penetration of nutrients and provides high surface area for attachment and proliferation of mammalian cells.[1,2] Previously, the preparation of Gel based cryogel was carried out in environmentally friendly way using enzymatic reaction under cryoconditions.[3] To prepare stable materials we developed a preparation method allowing avoid the use of toxic reducing agent borohydride for reduction of Schiff's base.[4] In this study we used dextran dialdehyde as a mild nontoxic cross-linker for preparation of cryogels based on different types of gelatin and chitosan. Additionally the cryogels were cross-linked via formation of polyelectrolyte complex(PEC) between oppositely charged groups of gelatine and chitosan. Physico-chemical properties, elastic modulus and degradation of the materials based on different ratios of dextran-gelatin and dextran-gelatin-chitosan at physiological conditions were investigated.

Human hepatic epithelial cell culture line and fibroblasts cells grow in the dextran-gelatin-chitosan cryogel scaffolds were studied. The type of gelatin significantly affected the migration, proliferation of cell and also microscopic morphology of the scaffold. The dextran-chitosan-gelatin (fish)(1:1:1wt %) based materials show better fibroblast growth compare to dextran-fish gelatin only. The cryogels containing dextran-chitosan-gelatin(bovine A)(1:1:1wt %) revealed good attachment and proliferation of hepatocytes inside of the material, whereas the cell line formed clusters on the surface of the PEC cryogel based on dextran-chitosan-gelatin(bovine A)(Fig. 1).




Figure 1. SEM images of gelatin-chitosan cryogel crosslinked by dextran dialdehyde: initial gel (a); with proliferated hepatocytes (b).

References:

- [1] Dainiak, M. B., Allan, I. U., Savina, I. N. et al. Gelatin–fibrinogen cryogel dermal matrices for wound repair: preparation, optimisation and in vitro study. *Biomaterials*, 31(1), (2010) 67-76.
- [2] Berillo, D., et al. "Oxidized dextran as crosslinker for chitosan cryogel scaffolds and formation of polyelectrolyte complexes between chitosan and gelatin." *Macromolecular bioscience* 12.8 (2012): 1090-1099.
- [3] Kirsebom H., et al. "Enzyme-Catalyzed Crosslinking in a Partly Frozen State: A New Way to Produce Supermacroporous Protein Structures." *Macromolecular bioscience* 13.1 (2013): 67-76.
- [4] Berillo, D., Volkova N.. "Preparation and physicochemical characteristics of cryogel based on gelatin and oxidised dextran." *Journal of Materials Science* 49.14 (2014): 4855-4868.

Keywords: Cell Proliferation, biomaterial, 3D scaffold, Polymeric material Conference: 10th World Biomaterials Congress, Montréal, Canada, 17 May - 22 May, 2016.

Presentation Type: Poster Topic: Synthetic scaffolds as extracellular matrices

Citation: Berillo D, Zheng Y and Savina IN (2016). CRYOGELS BASED ON POLYELECTROLYTE COMPLEX BETWEEN CHITOSAN AND GELATIN FORMED UNDER CRYOCONDITIONS FOR TISSUE ENGINEERING. *Front. Bioeng. Biotechnol. Conference Abstract: 10th World Biomaterials Congress*. doi: 10.3389/conf.FBIOE.2016.01.00149

Received: 27 Mar 2016; Published Online: 30 Mar 2016.

